

Predictions of thermomagnetic properties of TbAl₂ and GdAl₂ performed with ATOMIC MATTERS MFA Computation System.

RAFAŁ MICHAŁSKI, JAKUB ZYGADŁO
INDUFORCE

M.Pszona 41/29 31-462 Cracow

POLAND

JAGIELLONIAN UNIVERSITY,

Faculty of Mathematics and Computer Science,

Łojasiewicza 6 30-348 Cracow,

POLAND

r.michalski@induforce.eu <http://www.atomicmatters.eu>

Abstract: We present the results of non-free parameter calculations of properties of TbAl₂ and GdAl₂ single crystals, performed with our new computation system called ATOMIC MATTERS MFA [1,2]. A localized electron approach was applied to describe the electronic structure evolution of Tb and Gd ions over a wide temperature range and estimate Magnetocaloric Effect (MCE). Thermomagnetic properties of TbAl₂ and GdAl₂ were calculated based on the fine electronic structure of the 4f⁸ and 4f⁷ electronic configuration of the Tb and Gd ions, respectively. Our calculations yielded: magnetic moment value and direction; single-crystalline magnetization curves in zero field and in external magnetic field applied in various directions $\mathbf{m}(T, \mathbf{B}_{\text{ext}})$; the 4f-electronic components of specific heat $c_{4f}(T, \mathbf{B}_{\text{ext}})$; and temperature dependence of the magnetic entropy and isothermal entropy change with external magnetic field $-\Delta S(T, \mathbf{B}_{\text{ext}})$. The cubic universal CEF parameters values used for all CEF calculations was taken from [3] and recalculated for universal cubic parameters set for the RAl₂ series: $A_4 = +7.164\text{Ka}_0$ and $A_6 = -1.038\text{Ka}_0$. Magnetic properties were found to be anisotropic due to cubic Laves phase C15 crystal structure symmetry. These studies reveal the importance of multipolar charge interactions when describing thermomagnetic properties of real 4f electronic systems and the effectiveness of an applied self-consistent molecular field in calculations for magnetic phase transition simulation.

Key-Words: - TbAl₂, GdAl₂, RAl₂, Laves Phase, CEF, MFA, MCE, Atomic Matters.

1 Introduction

One of the biggest challenges in materials science is understanding and controlling the microscopic quantum mechanisms responsible for storing and releasing material entropy through controlled external magnetic field change processes. Our calculation methodology makes it possible to describe the thermomagnetic properties of magnetic materials, we decided to test our approach for TbAl₂ and GdAl₂ compounds. The material series RAl₂ compounds (R=Rare Earth) are intermetallic materials with interesting thermomagnetic properties [3]. In other words, the RAl₂ series of compounds are fascinating due to their large magnetocaloric entropy changes under external magnetic fields. This large change in MCE (Magnetocaloric Effect) is especially attractive in magnetic refrigeration due to its potential environmental friendliness compared to traditional gas refrigeration. We present the results of simulations of thermomagnetic properties of some RAl₂ compounds performed with our new

computation system called ATOMIC MATTERS MFA [1,2]. A few calculation results for TbAl₂ compound are compared with experimental data taken from the literature [3-6] and for GdAl₂ from papers [6,7]. All the lanthanides combine with aluminum to form RAl₂ compounds with the same crystalline structure [3]. All RAl₂ compounds are ferromagnetic at low temperatures [3]. RAl₂ crystals have the so-called cubic Laves phase C15 structure, while the point symmetry for rare earth ions is $4\bar{3}m$. The elementary cell of the crystal structure of Laves phase is presented in fig. 1. The CEF (Crystal Electric Field) parameters describing the multipolar charge interaction of R ions in the crystal surrounding in this structure was agreed for all compounds and established according to study of the DyAl₂ compound [3] for: $A_4 = +7.164\text{Ka}_0$ and $A_6 = -1.038\text{Ka}_0$. We decided to predict the properties of TbAl₂ and GdAl₂ completely without free parameters; therefore, we used the established cubic CEF and molecular field factor n_{mol} that is recalculated from DyAl₂.




Fig.1. Cubic elementary cell of RAl_2 Laves phase C15 crystals.

2 Computation system

All calculations for TbAl_2 and GdAl_2 were performed with ATOMIC MATTERS MFA computation system. This is extension of the ATOMIC MATTERS application [1] describes fine electronic structure and predicts basic magnetic and spectral properties of materials in a paramagnetic state. ATOMIC MATTERS MFA computation system [2] provides magnetic, calorimetric and spectroscopic properties of atomic-like localized electron systems under the influence of Crystal Electric Field (CEF), spin-orbit coupling, and magnetic interactions, taken both as dynamic Mean Field Approximation (MFA), calculations and the influence of established external magnetic field \mathbf{B}_{ext} [2]. ATOMIC MATTERS MFA provides macroscopic properties of materials in defined temperature regions, especially around the phase transition temperature: magnetic moment $\mathbf{m}(\mathbf{T}, \mathbf{B}_{\text{ext}})$ (spin and orbital, directional components), localized electron specific heat $c_{4f}(\mathbf{T}, \mathbf{B}_{\text{ext}})$, localized electron entropy with a useful tool set for MCE, isothermal entropy change $-\Delta S(\mathbf{T}, \mathbf{B}_{\text{ext}})$ calculations, evolution of energy level positions, total free energy, and more.

To enhance their ease of use and efficacy, both calculation systems implement an advanced Graphic User Interface (GUI) with a system of hierarchical tabs for managing calculation results, 3D interactive visualizations of potentials and fields based on Open Graphics Library (OpenGL), intuitive tools, and databases. More up-to-date information about Atomic Matters computation systems are available on our web page [8].

3 Theoretical background

ATOMIC MATTERS MFA computation system calculation methodology is deeply rooted in atomic physics. Taking into consideration the individual population of states of fine electronic structure of ions/atoms at different temperatures according L. Boltzmann statistics makes it possible to define the temperature dependencies of single ionic properties. ATOMIC MATTERS MFA can simulate phase transitions of ionic/atomic systems according to dynamic calculations of the molecular field \mathbf{B}_{mol} , simply defined as:

$$\mathbf{B}_{\text{mol}}(\mathbf{T}) = n_{\text{mol}} \mathbf{m}(\mathbf{T}) \quad (1)$$

that interacts with ions to induce their magnetic moments. Such self-consistent calculations can only be performed after establishing the molecular field factor n_{mol} that is closely related to the temperature of phase transitions, T_C .

For rapid calculations in a thermodynamically stable temperature region, ATOMIC MATTERS offers the following CEF+Spin-Orbit+Zeeman Hamiltonian according to the chosen calculation space of ground multiplet $|J, J_z\rangle$ or ground atomic term $|LSL_z S_z\rangle$ respectively[1]:

$$H_J = H_{\text{CEF}} + H_{\text{Zeeman}} = \sum_n \sum_m B_n^m \hat{\mathbf{O}}_n^m(J, J_z) + g_L \mu_B \mathbf{J} \cdot \mathbf{B}_{\text{ext}} \quad (2)$$

or

$$H_{LS} = H_{\text{CEF}} + H_{\text{S-O}} + H_{\text{Zeeman}} = \sum_n \sum_m B_n^m \hat{\mathbf{O}}_n^m(L, L_z) + \lambda \mathbf{L} \cdot \mathbf{S} + \mu_B (\mathbf{L} + g_e \mathbf{S}) \cdot \mathbf{B}_{\text{ext}} \quad (3)$$

For all Hamiltonians: B_n^m denotes CEF parameters, $\hat{\mathbf{O}}_n^m$ are Stevens operators, λ -is the spin-orbit constant, and g_L and $g_e \approx 2.002319$ are the gyromagnetic factors of a whole ion or single electron respectively. For a whole ion or electron respectively, μ_B is the Bohr magneton and \mathbf{B}_{ext} is the external magnetic field. In all cases, calculations in the $|LSL_z S_z\rangle$ space are more physically appropriate due to their completeness, but traditional calculations with base $|JJ_z\rangle$ can be also performed by our computation systems for comparisons and rapid estimations [2]. For calculating properties in temperatures around the magnetic phase transition point, a self-consistent methodology for molecular field calculation called Mean Field Approximations (MFA) is applied. The idea behind this method is to estimate the direction and value of the magnetic field (molecular field) generated by ions at a defined temperature, and to calculate the influence of this magnetic field for electronic state structures of ions. In a selected calculation space, according to eq.1 we define a molecular field as an expected value of the total moment of the 4f electronic subshell multiplied by the molecular field, inter ionic exchange factor n_{mol} :

$$\mathbf{B}_{\text{mol}} = -n_{\text{mol}} g_L \mu_B \langle \mathbf{J} \rangle \quad (4)$$

or

$$\mathbf{B}_{\text{mol}} = -n_{\text{mol}} \mu_B \langle \mathbf{L} + g_e \mathbf{S} \rangle \quad (5)$$

Where the gyromagnetic factors are g_L and $g_e \approx 2.002319$. On the basis of the calculated electronic level structure $E_i(T)$, the directional components of magnetic moments are established for all identical ions. This means that Hamiltonian matrix diagonalization is performed for all defined temperature steps recurrently. This is in contrast to simple ATOMIC MATTERS calculations [1], which diagonalize matrices one time for a single run and deduce all thermodynamic properties from the stable discrete energy level structure obtained. This self-consistent procedure provides temperature-dependent energy level structure and has one only free parameter, n_{mol} , called the molecular field parameter. The value of n_{mol} is closely related to the phase transition temperature T_C of the macroscopic structure of ions. The formal expression of the full Hamiltonian used by ATOMIC MATTERS MFA computation system, according to the chosen calculation space: $|JJ_z\rangle$ or $|LSL_zS_z\rangle$ respectively, has the form:

$$H_{J\text{mol}} = H_J + H_{\text{mol}} = \sum_n \sum_m B_n^m \hat{\mathbf{O}}_n^m(J, J_z) + n_{\text{mol}} g_L^2 \mu_B^2 \left(-\mathbf{J} \cdot \mathbf{J} + \frac{1}{2} \langle \mathbf{J} \rangle^2 \right) + g_L \mu_B \mathbf{J} \cdot \mathbf{B}_{\text{ext}} \quad (6)$$

or

$$H_{LS\text{mol}} = \sum_n \sum_m B_n^m \hat{\mathbf{O}}_n^m(L, L_z) + \lambda \mathbf{L} \cdot \mathbf{S} + n_{\text{mol}} \mu_B^2 \left(-(\mathbf{L} + g_e \mathbf{S}) \cdot (\mathbf{L} + g_e \mathbf{S}) + \frac{1}{2} \langle \mathbf{L} + g_e \mathbf{S} \rangle^2 \right) + \mu_B (\mathbf{L} + g_e \mathbf{S}) \cdot \mathbf{B}_{\text{ext}} \quad (7)$$

The eigenvectors of the Hamiltonian are described, according to the selected calculation base, by the total momentum quantum numbers $|JJ_z\rangle$ or spin and orbit quantum numbers $|LSL_zS_z\rangle$. Using the commutation relations of the angular momentum operators, we obtain information about expected values of the projections of magnetic momentum of all electronic states at a chosen temperature [2]:

$$m_J^\alpha(T) = \frac{g_L \mu_B}{Z(T)} \sum_i \langle J_\alpha^i \rangle \exp\left(-\frac{E_i(T)}{k_B T}\right) \quad (8)$$

$$m_{LS}^\alpha(T) = \frac{\mu_B}{Z(T)} \sum_i \langle L_\alpha^i + g_e S_\alpha^i \rangle \exp\left(-\frac{E_i(T)}{k_B T}\right) \quad (9)$$

Where: α indexes directional components, i numbers the Hamiltonian eigenstates, while Γ_i represents the expected value of the total angular momentum along the α -axis in the i -th state:

$$\langle J_\alpha^i \rangle = \langle \Gamma_i(T) | \mathbf{J}_\alpha | \Gamma_i(T) \rangle \quad (10)$$

$$\langle L_\alpha^i + g_e S_\alpha^i \rangle = \langle \Gamma_i(T) | \mathbf{L}_\alpha + g_e \mathbf{S}_\alpha | \Gamma_i(T) \rangle \quad (11)$$

All property calculations can be done for 3D (x,y,z) real space by using complex Hamiltonian matrix elements defined by full expressions of extended Stevens \mathbf{O}_n^m operators[9]. Mostly for comparison with traditional calculation results, ATOMIC MATTERS also offers a 2D (x,z) calculation methodology of a simplified model of CEF interactions defined by Stevens \mathbf{O}_n^m operators with real number matrix elements only [10].

Taking into consideration the possibility of the thermal population of states, we automatically obtain the thermal evolution of single ion properties of the whole compound [11,12].

Under the thermodynamic principle at temperature $T=0K$, only the ground state is occupied. In this situation, the magnetic moment of the ion is exactly equal to the momentum of the ground state. If the temperature rises, the probability of occupying higher states increases according to Boltzmann statistics. The number of ions with energy E_i within a system at temperature T is:

$$N_i(T) = N_0 \frac{\exp\left(-\frac{E_i(T)}{k_B T}\right)}{Z(T)} \quad (12)$$

where $N_0 \approx 6.022.1023 \text{ mol}^{-1}$ (Avogadro constant) and $Z(T)$ is the sum of states. Knowing the sum of the states, we can determine the Helmholtz free energy $F(T)$:

$$F(T) = -k_B T \ln Z(T) \quad (13)$$

According to thermodynamic principles, the contribution of localized electrons to the total specific heat of materials can be calculated by numerical derivation of Helmholtz free energy:

$$c_{\text{mol}}(T) = -T \left(\frac{\partial^2 F(T)}{\partial T^2} \right) \quad (14)$$

This makes it possible to calculate entropy according to the well-known definition:

$$S(T) = S(0) + \int_0^T \frac{c(T)}{T} dT \quad (15)$$

The value of electronic entropy for a defined temperature is difficult to compare, but the isothermal change of the entropy of the system at a given temperature is a very important material parameter that describes its thermomagnetic properties. Isothermal Entropy change $-\Delta S(T, B_{\text{ext}})$, captured for different temperatures under the influence of different magnetic fields, is one the most important properties of a material that

describes its usefulness as a magnetocaloric material. The value $\Delta S(T, B_{\text{ext}})$, extracted from experimental specific heat measurements, is often presented as a basic description of the Magnetocaloric Effect (MCE) of a material [3-7]. In our approach, isothermal entropy change can be directly calculated from eq. 15 according to the definition:

$$-\Delta S(T, B_{\text{ext}}) = S(T, B_{\text{ext}}=0) - S(T, B_{\text{ext}}). \quad (16)$$

ATOMIC MATTERS MFA also provides single-ionic magnetocrystalline anisotropy calculations that include full calculations (without Brillouin function approximation) of $K_i(T)$ magnetocrystalline constants for defined temperature ranges according to the relations [15]:

$$\begin{aligned} K_1(T) &= \frac{3}{2} B_2^0 \langle \hat{\mathbf{O}}_2^0 \rangle - \langle \hat{\mathbf{O}}_2^2 \rangle - 5 B_4^0 \langle \hat{\mathbf{O}}_4^0 \rangle - 3 \langle \hat{\mathbf{O}}_4^2 \rangle - \\ &\quad - \frac{21}{2} B_6^0 \langle \hat{\mathbf{O}}_6^0 \rangle - 5 \langle \hat{\mathbf{O}}_6^2 \rangle, \\ K_2(T) &= \frac{35}{8} B_4^0 \langle \hat{\mathbf{O}}_4^0 \rangle - 4 \langle \hat{\mathbf{O}}_4^2 \rangle + \langle \hat{\mathbf{O}}_4^4 \rangle + \\ &\quad + \frac{63}{8} B_6^0 \langle \hat{\mathbf{O}}_6^0 \rangle - 20 \langle \hat{\mathbf{O}}_6^2 \rangle + 5 \langle \hat{\mathbf{O}}_6^4 \rangle, \\ K_2^*(T) &= \frac{1}{8} (B_4^0 \langle \hat{\mathbf{O}}_4^0 \rangle + 5 B_6^0 \langle \hat{\mathbf{O}}_6^0 \rangle), \\ K_3(T) &= -\frac{231}{16} B_6^0 \langle \hat{\mathbf{O}}_6^0 \rangle, \quad K_3^*(T) = -\frac{11}{16} B_6^0 \langle \hat{\mathbf{O}}_6^4 \rangle. \end{aligned} \quad (17)$$

Where: $\langle \hat{\mathbf{O}}_n^m \rangle$

denotes thermal expected values of Stevens operators we defined according to C. Rudowicz [9]. The exchange interactions simulated according to MFA methodology defined by eq. 1 provides simulated properties strongly dependent on the only parameter n_{mol} that is closely related to the temperature of phase transitions: T_C . It is easy to find the value of n_{mol} for correct T_C , but the value of this parameter can be estimated according to De Gennes scaling [10]:

$$T_C \sim G(f^n), \quad G(f^n) = (g_L - 1)^2 J(J+1) \quad (18)$$

De Gennes scaling is also a useful tool for n_{mol} estimation, as charge surroundings can be transferred between ions in series. The CEF part of Hamiltonian contains Stevens CEF parameters B_n^m . The values of these parameters are only appropriate for the defined ion. The recalculation of B_n^m parameters defined for an ion A in the crystal lattice surrounding of ion B in the same crystalline position follows the simple scheme:

$$B_n^m(\text{ion A}) \rightarrow A_n^m \rightarrow B_n^m(\text{ion B}) \quad (19)$$

Stevens B_n^m parameters can be expressed by universal A_n^m parameters, according to the calculation space used, as follows:

$$\begin{aligned} |J, J_z\rangle; \quad B_n^m(J, J_z) &= \theta_n(J) \langle r_{4f}^n \rangle A_n^m \\ |L, S, S_z, L_z\rangle; \quad B_n^m(L, L_z) &= \theta_n(L) \langle r_{4f}^n \rangle A_n^m \end{aligned} \quad (20)$$

Where values of the 2nd, 4th and 6th power of average radius of a/the 4f shell $\langle r^n \rangle$ have been calculated by many authors using Hartree-Fock-type methodology, and the results can be easily found in the literature. The θ_n parameters are the J or L dependent Clebsh-Gordan-type factors, sometimes called α, β, γ Stevens factors $\theta_2=\alpha$, $\theta_4=\beta$, $\theta_6=\gamma$, which can be expressed by finite equations available in [11-13]. The values of $\langle r_{4f}^n \rangle$ are collected in the system's open database together with a reference. In all presented calculations for R ions, we used the $\langle r_{4f}^n \rangle$ values tabulated in [13]. The ability to recalculate CEF parameters between ions and calculation spaces offers a unique chance to establish an acceptable simplification of methodology. The recalculation of CEF parameters in Atomic Matters systems is fully automated, but an explicit Stevens Factors Calculator is also available.

4 Calculation results

In this section, we present the results of an investigation of the magnetic and magnetocaloric properties of a TbAl₂ and GdAl₂ single crystal. The predictions of properties are completely achieved without free parameters. We use established cubic CEF for DyAl₂ [parallel paper] parameters in Stevens notation [3] $B_4 = -(5.5 \pm 1.2) \cdot 10^{-5}$ meV and $B_6 = -(5.6 \pm 0.8) \cdot 10^{-7}$ meV. We recalculated values of Stevens parameters to universal, ion-independent CEF notation A_n^m according to eq. 19 and eq. 20. We assume that the parameters $A_4 = +7.164 K a_0$ and $A_6 = -1.038 K a_0$ that are obtained in this way define the charge surroundings of an R ion in a crystal lattice of RAl₂. The visualization of such defined potential is shown in fig. 2. The triangular shapes, which related with the location of the coordinating Al ions, are located symmetrically in cubic surroundings and reflect the atom position visible in the elementary cell of Laves phase shown in fig. 2.




Fig.2. Crystal Field potential visualization of cubic surrounding of R-ions in RAl_2 , defined by CEF parameters: $A_4 = +7.164Ka_0$ and $A_6 = -1.038Ka_0$. The visualization of positive sign potential is externally cut off by the cube.

We attributed the magnetism of $TbAl_2$ to Tb and the magnetism of $GdAl_2$ to the Gd ions and performed calculations of the fine electronic structure of the $4f^8$ and $4f^7$ electronic systems, respectively. All calculations was performed for cubic symmetry, taking into account the crystal field and inter-site, spin-dependent exchange interactions. The energy level scheme derived is associated with the reduction of the degeneracy of the lowest atomic term (2F and 8S for Tb and Gd ions, respectively) given by Hund's first two rules. The value of molecular field factor n_{mol} for $TbAl_2$ and $GdAl_2$ was established according to $n_{mol}^{Dy} = 3.6T/\mu_B$ for $DyAl_2$ and de Gennes scaling eq. 18 [10]. The comparison between experimentally found Curie temperature T_C and de Gennes scaling is shown in fig.3.




Fig.3. De Gennes scaling of Curie temperature T_C for all rare-earth ions in series RAl_2 in comparison to experimental data from ref.[3].

Experimental values of T_C for RAl_2 compounds [3-7] and the theory are in good agreement for 'heavy Rare Earths' elements from Gd ($4f^7$) to Yb ($4f^{14}$). De Gennes relations [10,14] makes it possible to establish molecular field factor for $TbAl_2$ $n_{mol}^{Tb} = 7.0T/\mu_B$ and for $GdAl_2$ $n_{mol}^{Gd} = 17.0T/\mu_B$.

4.1 Calculated anisotropic properties of $TbAl_2$ single crystals.

The electronic configuration of ^{65}Tb atoms consists of a closed shell inactive atomic core [$_{54}Xe$], electronic system $4f^8$ and 'outer electrons $5d^16s^2$ '. We attributed the magnetic properties of $TbAl_2$ compound as an effect of properties of $4f^8$ electronic system under influence of electromagnetic interactions defined according to the description in the theory section. The starting point of our analysis is the ground atomic term 2F with quantum number of orbital angular momentum $L=3$ and total spin $S=3$.

The full calculated energy level structure in $|L,S,L_z,S_z\rangle$ calculation space is shown in fig. 4. The obtained overall splitting is strongly dependent on the strength of spin-orbit intra-atomic interactions. We used free-ion value of spin orbit constant of Tb^{3+} ions $\lambda = -410K$ [13] and obtained overall splitting of 2F atomic term at about $8620K = 0.743 eV$.




Fig.4. The result of calculation of energy level positions vs. temperature of the fine electronic structure of $4f^8$ electronic configuration of Tb ions in $TbAl_2$ in $|L,S,L_z,S_z\rangle$ space under the influence of intra-atomic spin-orbit coupling, inter-atomic self-consistent molecular magnetic field and Crystal Electric Field (CEF).

Details of ground states structure are shown in fig.5.




Fig.5. The result of calculation of ground multiplet energy levels structure vs. temperature calculated vs. temperature of the fine electronic structure of $4f^8$ electronic configuration of Tb ions in TbAl_2 in $|L, S, L_z, S_z\rangle$. At Curie temperature $T_C = 105\text{K}$ structure splits under the influence of molecular field.

In the absence of an external magnetic field, the induced molecular field splits and moves into degenerated states. The value of the molecular field factor established for TbAl_2 which reproduce T_C well at about 105K is $n_{\text{mol}} = 7.0\text{T}/\mu_B$.




Fig. 6. Ground multiplet energy levels structure vs. temperature calculated for $4f^8$ electronic system of Tb ions in TbAl_2 under the influence of a small external magnetic field of 0.01T applied along crystal direction [111].

Above T_C , in a paramagnetic state, the ground state is degenerated. The ground quartet consists of two quasi doublets. The wave functions of ground state of Tb ($4f^8$ electronic system) ions in TbAl_2 in a

paramagnetic state can be expressed in $|Jz\rangle$ notation as:

$$\begin{aligned}\Gamma_1 &= +0.661|-4\rangle -0.353|0\rangle +0.6614|+4\rangle \\ \Gamma_2 &= -0.151|-6\rangle -0.691|-2\rangle +0.691|+2\rangle +0.151|+6\rangle \\ \Gamma_3 &= -0.450|-3\rangle +0.381|+1\rangle +0.807|+5\rangle \\ \Gamma_4 &= -0.450|+3\rangle +0.381|-1\rangle +0.808|-5\rangle\end{aligned}$$

A molecular field split these states at $T < T_C$. The value of the molecular field changes, and at $T=0$ (absolute zero) $B_{\text{mol}} = 42\text{T}$ and its direction is along crystal direction [110]. In this condition, the wave function of a ground singlet gets the form:

$$\begin{aligned}\Gamma_0 &= -0.358|-6\rangle +0.567|-5\rangle -0.553|-4\rangle +0.407|-3\rangle - \\ &0.247|-2\rangle +0.122|-1\rangle -0.04|0\rangle +0.003|+1\rangle +0.006|+2\rangle - \\ &-0.004|+3\rangle +0.001|+4\rangle -0.0002|+5\rangle +0.0001|+6\rangle\end{aligned}$$

The electronic structure obtained in the absence of an external magnetic field is extremely fragile; even a small magnetic field applied along direction [100] or [111] forces the structure to change the order of states and creates an anomaly at low temperatures. The influence of a small external magnetic field applied along direction [111] for the structure of the lowest electronic states is shown in fig. 6. The position of this anomaly corresponds with peaks on specific heat curves. The calculated specific heat for a TbAl_2 single crystal under the influence of an external magnetic field applied along various crystal directions is presented in fig. 7, fig. 8 and fig. 9.




Fig. 7. Calculated $4f$ -electron component of molar specific heat (eq.14) with Debye crystal lattice component ($\theta = 350\text{K}$) vs. temperature for Tb ions in TbAl_2 , under the influence of an external magnetic field applied along direction [100].




Fig. 8. Calculated 4f-electron component of molar specific heat (eq.14) with Debye crystal lattice component ($\theta=350\text{K}$) vs. temperature for Tb ions in TbAl_2 , under the influence of an external magnetic field applied along [111] direction.




Fig. 9. Calculated 4f-electron component of molar specific heat (eq.14) with Debye crystal lattice component ($\theta=350\text{K}$) vs. temperature for Tb ions in TbAl_2 , under the influence of an external magnetic field applied along direction [111].

The closer look at the unusual behaviour of the 4f- electron component of specific heat simulated under the influence of an external magnetic field along ‘diagonal’ direction [111] is shown in fig.10.




Fig. 10. Calculated 4f-electron component of molar specific heat vs. temperature for Tb ions in TbAl_2 , under the influence of an external magnetic field applied along direction [111] from 0 up to 7.5T.

We have not found comparative experimental data for specific heat measurements, but F. W. Wang [5] provides data of measured specific heat change $\Delta c(T, B_{\text{ext}})$ defined as:

$$\Delta c(T, B_{\text{ext}}) = c(T, B_{\text{ext}}) - c(T, 0) \quad (21)$$

for measurements for $\Delta B_{\text{ext}}=5\text{T}$. Comparison between data from [5] and our simulations of $\Delta c(T, B_{\text{ext}})$ is shown in fig.11. The simulation for $\Delta B_{\text{ext}}=5\text{T}$ in this figure is represented by a solid line.




Fig. 10. Calculated specific heat change vs. temperature for Tb ions in TbAl_2 , under the influence of an external magnetic field applied along direction [111] from 0 to 7.5T, with step 0.5T in comparison with experimental data from [5]. Solid line represents simulation for $\Delta B_{\text{ext}}=0.5\text{T}$.

Collected data of specific heat makes it possible to calculate isothermal entropy change $-\Delta S(T, B_{\text{ext}})$ according to eq.16, the same methodology as used by experimentalist [3-7]. Isothermal entropy changes calculated with various external magnetic fields applied along all main directions of the/a cubic structure are presented in fig. 11, fig.12 and fig.13.




Fig. 11. Calculated isothermal entropy change of 4f-electronic system vs. temperature (eq.16) of Tb ions in TbAl_2 , under the influence of various external magnetic field values from 0 to 7.5T, with step 0.5T applied along direction [100].




Fig.12. Calculated isothermal entropy change of 4f-electronic system vs. temperature (eq.16) of Tb ions in TbAl_2 , under the influence of various external magnetic field values from 0 to 7.5T, with step 0.5T applied along direction [110].




Fig.13. Calculated isothermal entropy change of 4f-electronic system vs. temperature (eq.16) of Tb ions in TbAl_2 , under the influence of various external magnetic field values from 0 to 0.5T with step 0.1T and 7.5T with step 0.5T applied along direction [111].

The anisotropic behavior of calculated thermomagnetic properties is reflected in magnetocrystalline anisotropy constant calculations. The results of $K_i(T)$ calculations according to eq.17 in the absence of an external magnetic field are shown in fig. 14.




Fig.14. Calculated according to eq. 17 magnetocrystalline anisotropy constants K_1 , K_2 and K_3 vs. temperature, for Tb ions in TbAl_2 in absence of an external magnetic field.




Fig. 14. Calculated according to eq. 17 magnetocrystalline anisotropy constants K_1 , K_2 and K_3 vs. temperature, for Tb ions in TbAl_2 under the influence of small external magnetic field $B_{\text{ext}}=0.01\text{T}$, applied along direction $[111]$.

For completeness, magnetic moment calculations vs. temperature under various external magnetic field conditions were performed. The results of $\mathbf{m}(T, B_{\text{ext}})$ are presented in fig. 15, fig. 16 and fig. 17. The simulated thermal evolution of magnetic moment components under the influence of external magnetic field along direction $[110]$ shown in fig. 16 clearly confirms direction $[110]$ as an easy magnetization axis of TbAl_2 . The applied external magnetic field along this direction confirms perfect parallel directions of magnetic vector and external magnetic field (note: in cubic symmetry $[110]=[011]=[101]$).




Fig. 15. Calculated x,y,z-directional components of total magnetic moment vs. temperature, calculated for Tb ions in TbAl_2 under the influence of CEF and molecular magnetic field and various values of external magnetic field from 0 to 7.5T with step 0.5T applied along direction $[100]$.




Fig. 16. Calculated x,y,z-directional components of total magnetic moment vs. temperature, calculated for Tb ions in TbAl_2 under influence of CEF and molecular magnetic field and various values of external magnetic field from 0 to 7.5T with step 0.5T applied along direction $[110]$.




Fig. 17. Calculated x,y,z-directional components of total magnetic moment vs. temperature, calculated for Tb ions in TbAl_2 under influence of CEF and molecular magnetic field and various values of external magnetic field from 0 to 7.5T with step 0.5T applied along direction $[111]$.

Magnetic moment calculated in external magnetic field parallel to $[111]$ and $[100]$ direction reveals unusual behavior of the directional component of total moment. Similar behavior of magnetic moment directions was reported in ref. [4], but most of the presented results of calculations of properties of TbAl_2 still await experimental verification.

We found only a few reports about measurements of thermomagnetic properties of TbAl_2 single crystals. Some experimental comparative data of isothermal

entropy change measured on TbAl₂ single crystals is provided by P.O. Ribeiro et al. [4,6], and interesting specific heat change measured on polycrystalline sample is provided by F.W. Wang et al. [5]. All experimental data from [3-6] confirms the correctness of our approach in thermomagnetic properties of TbAl₂.

4.2 Calculation of isotropic properties results for GdAl₂ crystals.

The electronic configuration of Gd atoms consists of a closed shell inactive atomic core [₅₄Xe], a half filled 4f shell (e.g electronic system 4f⁷), and 'outer electrons 5d¹6s²'. We attribute the magnetic properties of GdAl₂ compound to be an effect of properties of 4f⁷ electronic system under the influence of electromagnetic interactions defined according to the description in the theory section. The starting point of our analysis is the ground atomic term ⁸S with quantum number of orbital angular momentum L=0 and total spin S=7/2. This means Gd is a pure spin system. According to this, CEF does not interact with electronic states of ground atomic term ⁸S. In consequence, according to our approach, there is no source of single ionic anisotropy in a Gd electronic system. Inter-atomic magnetic interactions according to our MFA approach have pure isotropic nature eq.4 and eq.5, therefore the obtained properties of GdAl₂ are absolutely identical despite the direction of the magnetic field applied. The value of molecular field factor n_{mol} for GdAl₂ was established according to de Gennes scaling [10] $n_{\text{mol}}^{\text{Gd}} = 17.0\text{T}/\mu_{\text{B}}$. The calculated energy level structure is shown in fig. 17.




Fig. 17. The result of calculation of energy level positions vs. temperature of the fine electronic structure of 4f⁷ electronic configuration of Gd ions in GdAl₂ under the influence of inter-atomic self-

consistent molecular magnetic field and Crystal Electric Field (CEF).

In the absence of an external magnetic field, the ground term of a 4f⁷ electronic system is fully degenerated. A self-consistent molecular field splits these states at T<T_C. The value of the molecular field changes, and at T=0 (absolute zero) B_{mol}=63T. The influence of the external magnetic field B_{ext}=6T on the structure of states is shown in fig. 18.




Fig. 18. Calculated energy level structure of 4f⁷ electronic configuration of Gd ions vs. temperature under the influence of external magnetic field 6T.

The energy level structure makes it possible to calculate the 4f-electron component of specific heat. The result of calculation of specific heat under the influence of an external magnetic field compared to experimental data from ref. [7] is shown in fig. 19. The calculations of electronic structure under the influence of an external magnetic field applied along [111] direction was also performed. The energy level structure calculated for the external magnetic field in this direction does not contain anomalies and is similar to calculations performed for B_{ext} along easy direction [100], as shown in fig.5. Specific heat calculated in this condition is shown in fig.8.




Fig.19. Calculated 4f-electron component of molar specific heat (eq.14) with Debye crystal lattice component ($\theta=350\text{K}$) vs. temperature of Gd ions in GdAl_2 , under the influence of external magnetic field from 0 to 6T with step 0.2T. Inset: experimental data from ref. [7]

Collected specific heat data makes it possible to calculate isothermal entropy change $-\Delta S(T, B_{\text{ext}})$ according to eq.16, the same methodology as used by experimentalist [3-7]. Isothermal entropy change calculated with various external magnetic fields is presented in fig. 9, fig. 10 and fig. 11. The reference data taken from experimental measurement [3] is shown in the insets.




Fig. 20. Calculated isothermal entropy change of 4f-electronic system vs. temperature (eq. 16) of Gd ions in GdAl_2 , under the influence of various values of external magnetic fields from 0 to 7.5T, with step 0.5T. Inset: isothermal entropy change obtained from experimental data, taken from [7]. Congruent with experimental, calculated for $\Delta B_{\text{ext}}=2$ and $\Delta B_{\text{ext}}=5$ T lines are solid lines.

The isotropic behavior of calculated thermomagnetic properties agrees with experimental data [6,7].

For completeness, magnetic moment calculations vs. temperature under various external magnetic field conditions was performed. The results of $m(T, B_{\text{ext}})$ are presented in fig. 21.




Fig.13. Calculated uni-directional total magnetic moment vs. temperature, calculated for Gd ions in GdAl_2 under the influence of molecular magnetic field and various values of external magnetic field from 0 to 6.0T with step 0.2T.

5 Conclusions

We performed calculations for GdAl_2 and TbAl_2 thermomagnetic properties using the ATOMIC MATTERS MFA computation system. The local symmetry of the Gd ions is cubic, which significantly simplifies the analyses. All the calculations were performed without free parameters. Very good agreement was obtained between thermomagnetic properties and experimental data. This confirms the effectiveness of our theoretical approach. Working with ATOMIC MATTERS MFA revealed its high usefulness. The visual form of calculation results, full 3D interactive CEF potential visualization, intuitive tools for convention and unit recalculation, and the ability to compare data results all allow the user to utilize the power of the application very effectively. In conclusion, we confirm that ATOMIC MATTERS MFA is a unique application that combines a package of tools for correctly describing the physical properties of atomic-like electron systems subjected to electromagnetic interactions in real materials. This is an accurate tool for calculating properties of ions under the influence of the electrostatic potential of definable symmetry and both external and inter-ionic magnetic fields taken

as a mean field approximation in magnetically ordered state.

This paper is the second in a series devoted to the RAI_2 (R=rare earth) compounds family. The same set of parameters will be used for heavy rare earth elements: Dy, Ho, Er and Tm in this crystal structure in the next paper. Molecular field factor will be recalculated according to de Gennes scaling [10].

References:

- [1] Rafal Michalski, Jakub Zygałło. *Describing the Fine Electronic Structure and Predicting Properties of Materials with ATOMIC MATTERS Computation System*. Proceedings: 18th Int. Conf. on Physics, Mathematics and Computer Science - Dubai UAE 01.06.2016. <http://waset.org/publications/10004653/pdf>.
- [2] Rafal Michalski, Jakub Zygałło, *Thermal dependences of single ionic, magnetic properties of materials in ordered state, calculated with ATOMIC MATTERS MFA computation system*— Proceedings: 7th IIF-IIR International Conference on Magnetic Refrigeration at Room Temperature, **Thermag VII** - Torino ITALY, 11-14 September 2016.
- [3] H.G. Purwins and A. Leson, *Adv. Phys.* **39** (1990) 309.
- [4] P.O.Ribeiro, B.P.Alho, T.S.T.Alvarenga, E.P.Nóbrega, V.S.R.deSousa, A.Magnus G.Carvalho, A.Caldas, N.A.deOliveira, P.J.vonRanke *Journal of Magnetism and Magnetic Materials* **379** (2015)112–116.
- [5] F. W. Wang, X. X. Zhang, and F. X. Hu, *Appl. Phys. Lett.*, Vol. **77**, No. 9 (2000)1360.
- [6] P.O.Ribeiro, B.P.Alho, T.S.T.Alvarenga, E.P.Nóbrega, V.S.R.deSousa, A.Magnus G.Carvalho, A.Caldas, N.A.deOliveira, P.J.vonRanke, *Journal of Alloys and Compounds* **563** (2013) 242–248.
- [7] S. Yu Dankov, V. V. Ivchenko, A. Tishin, V. K. Pecharsky, *Magnetocaloric Effect in GdAl_2 and $\text{Nd}_2\text{Fe}_{17}$* , conference paper: *Advances in Cryogenic Engineering (Materials)*, **46**, (2000). 397-404A.
- [8] Software website: www.atomicmatters.eu
- [9] C. Rudowicz, C. Y Chung, *The generalization of the extended Stevens operators*, *J. Phys.: Condens. Matter* **16** (2004) 5825–5847.
- [10] P.G.de Gennes *J.Phys.Radiat* **23** (1962) 5010.
- [11] M. T. Hutchings, *Solid State Phys.* **16** (New York (1964) 227.
- [12] B. G. Wybourne, *Symmetry Principles and Atomic Spectroscopy*, J. Wiley and Sons, New York (1970).
- [13] A. Abragam and B. Bleaney, *EPR of Transition Ions*, Clarendon Press, Oxford (1970).
- [14] J.J.M. Franse, R.J. Radwanski; *Magnetic properties of binary rare-earth...* in *Handbook of Magnetic Materials* Vol **7**. Edited K.H.J.Bushow (1993) 307-500.
- [15] R. J. Radwański, R. Michalski, Z. Ropka, A. Blaut., *Physica B* **319** (2002) 78–89
- [16] B.Szpunart and P.A.Lindgard, *J. Phys. F: Metal Phys.* Vol. **9**. No. 3. 1979.